

Amendments to the Claims

This listing of claims replaces all prior versions and listings of claims in the application:

1. (Currently Amended) A multi-layer high temperature superconductor, comprising:
  - a first high temperature superconductor coated element, comprising:
    - a first substrate;
    - at least one first buffer deposited on the first substrate;
    - at least one first high temperature superconductor layer supported by the first buffer; and
    - a first metallic cap layer supported by the first high temperature superconductor layer; and
  - a second high temperature superconductor coated element, comprising:
    - a second substrate;
    - at least one second buffer deposited on the second substrate;
    - at least one second high temperature superconductor layer supported by the second buffer; and
    - a second metallic cap layer supported by the second high temperature superconductor layer;wherein the first and second high temperature superconductor coated elements are joined at the first and second metallic cap layers.
2. (Original) The superconductor of claim 1, wherein the first substrate is biaxially textured.
3. (Original) The superconductor of claim 2, wherein the biaxial texturing is by deformation texturing.

4. (Original) The superconductor of claim 3, wherein the first substrate comprises nickel.

5. (Original) The superconductor of claim 4, wherein the first substrate comprises nickel-chromium, nickel-copper, or nickel-vanadium alloys.

6. (Original) The superconductor of claim 5, wherein the first substrate comprises a nickel-chromium alloy.

7. (Original) The superconductor of claim 2, wherein the at least one first buffer is epitaxially deposited.

8. (Original) The superconductor of claim 1, wherein the at least one first buffer comprises metal oxides.

9. (Original) The superconductor of claim 8, wherein the metal oxides comprise cerium oxide and gadolinium oxide.

10. (Original) The superconductor of claim 8, wherein the first buffer further comprises yttria stabilized zirconia.

11. (Original) The superconductor of claim 1, wherein at least two buffers are sequentially deposited on the first substrate.

12. (Original) The superconductor of claim 11, wherein three buffers are sequentially deposited on the first substrate.

13. (Original) The superconductor of claim 1, wherein the first high temperature superconductor layer comprises metal oxide.

14. (Original) The superconductor of claim 1, wherein the first high temperature superconductor layer comprises rare earth oxides.

15. (Original) The superconductor of claim 14, wherein the rare earth oxides have the formula  $(RE)Ba_2Cu_3O_{7-\delta}$ , wherein RE is selected from the group consisting of rare earth elements and yttrium, and  $\delta$  is a number greater than zero and less than one.

16. (Currently Amended) The superconductor of claim 1, wherein the first metallic cap layer is deposited on the first high temperature superconducting layer.

17. (Original) The superconductor of claim 1, wherein the first and second substrates are of substantially identical composition.

18. (Original) The superconductor of claim 1, wherein the first and second buffers are of substantially identical composition.

19. (Original) The superconductor of claim 1, wherein the first and second high temperature superconducting layers are of substantially identical composition.

20. (Currently Amended) The superconductor of claim 1, wherein the first and second metallic cap layers are of substantially identical composition.

21. (Original) The superconductor of claim 1, wherein the first and second high temperature superconductor coated elements are of substantially identical composition.

22. (Currently Amended) The superconductor of claim 1, wherein the first and second metallic cap layers are continuously joined at their uppermost surfaces.

23. (Currently Amended) The superconductor of claim 1, wherein the first and second metallic cap layers are a single continuous layer.

24. (Original) The superconductor of claim 1, wherein the superconductor is in the form of a tape.

25. (Original) The superconductor of claim 1, wherein the substrates are substantially untextured, and the buffers and high temperature superconductor layers are biaxially textured.

26. (Original) The superconductor of claim 24, wherein the first and second high temperature superconductor coated elements are registered at their respective edges.

27. (Original) The superconductor of claim 24, wherein the first and second high temperature superconductor coated elements are offset along their lengths.

28. (Currently Amended) The superconductor of claim 27, wherein at least one of the first and second metallic cap layers extends along the edge of at least the first and second high temperature superconductor coated element.

29. (Original) The superconductor of claim 1, wherein the superconductor comprises a multifilamentary structure.

30. (Original) The superconductor of claim 29, wherein the first and second high temperature superconducting layers are divided into a plurality of filaments.

31. (Currently Amended) The superconductor of claim 1, further comprising a stabilizer, wherein the first and second metallic cap layers are joined to opposing surfaces of the stabilizer.

32. (Canceled)

33. (Canceled)

34. (Currently Amended) The superconductor of claim 1, further comprising a solder layer positioned between the first and second metallic cap layers.

35. (Currently Amended) The superconductor of claim 34, wherein the first metallic cap layer is directly joined to the solder layer.

36. (Currently Amended) The superconductor of claim 35, wherein the second metallic cap layer is directly joined to the solder layer.

37. (Currently Amended) The superconductor of claim 1, wherein the first metallic cap layer comprises multiple layers.

38. (Previously Presented) The superconductor of claim 37, wherein the multiple layers comprise:

- a first metal layer; and
- a second metal layer.

39. (Previously Presented) The superconductor of claim 38, wherein the first metal layer comprises silver and the second metal layer comprises copper.

40. (Currently Amended) The superconductor of claim 37, wherein the second metallic cap layer comprises:

- a third metal layer; and
- a fourth metal layer.

41. (Previously Presented) The superconductor of claim 40, wherein the third metal layer comprises silver and the fourth metal layer comprises copper.